



CT Gasket & Polymer Co., Inc.

DEL 8819 Emmott Rd, Houston, TX 77040

MAIL P.O. Box 40940, Houston, TX 77240-0940

TEL (713) 856-8667 / (800) 299-1685

FAX (713) 856-7317

WEB www.ctgasket.com

Hypalon[®] 60

Hypalon[®] provides good resistance to ozone and excellent resistance to abrasion, weather, and heat. The oil resistance characteristics of Hypalon are similar to neoprene. It has a service temperature range of **-20° F to 250° F.**

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	UNITS	VALUE
Specific Gravity	(G/CC)	1.47
Durometer: Shore 'A'	(pts)	60-70
Elongation	(%)	200
Tensile	(psi)	1500

The physical properties shown above were obtained on molded ASTM samples. They are typical, but they should not be used to set Quality Control Specification minimum requirements.