



CT Gasket & Polymer Co., Inc.

DEL 8819 Emmott Rd, Houston, TX 77040

MAIL P.O. Box 40940, Houston, TX 77240-0940

TEL (713) 856-8667 / (800) 299-1685

FAX (713) 856-7317

WEB www.ctgasket.com

Silicone UL60

UL Grade silicone sheeting is designed to be used in applications where the material is required to be listed with Underwriters Laboratories. The base silicone polymers used to make this material are listed with U.L. Capable of meeting UL94HB, ZZR-765, CL2A & 2B GR60, AMS 3303, and ASTM D200. It has a service temperature range of -103° F to 500° F.

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	UNITS	VALUE
Specific Gravity	(G/CC)	1.45
Durometer: Shore 'A'	(pts)	55-65
Elongation	(%)	400
Tensile Strength	(psi)	900
Tear Resistance (ASTM D624)	(psi)	120

The physical properties shown above were obtained on molded ASTM samples. They are typical, but they should not be used to set Quality Control Specification minimum requirements.