



CT Gasket & Polymer Co., Inc.

DEL 8819 Emmott Rd, Houston, TX 77040

MAIL P.O. Box 40940, Houston, TX 77240-0940

TEL (713) 856-8667 / (800) 299-1685

FAX (713) 856-7317

WEB www.ctgasket.com

Butyl

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	UNITS	VALUE
ASTM-D-2000 Classification		AA
Chemical Definition	Chloro-Isobutylene Isoprene	
Durometer	<i>(Shore A)</i>	60 +/-5
Tensile Strength	<i>(psi)</i>	1000
Elongation	<i>(% Min)</i>	300
Low Temperature	<i>°F</i>	-30
High Temperature	<i>°F</i>	275
Abrasion Resistance		Good
Oil Resistance		Poor
Sunlight Aging		Very Good

The physical properties shown above are typical, but they should not be used to set Quality Control Specification minimum requirements. Please see the CTG Chemical Resistance Guide for general chemical resistance and affect.