



CT Gasket & Polymer Co., Inc.

TEL (713) 856-8667 / (800) 299-1685

DEL 8819 Emmott Rd, Houston, TX 77040

FAX (713) 856-7317

MAIL P.O. Box 40940, Houston, TX 77240-0940

WEB [www.ctgasket.com](http://www.ctgasket.com)

# Hypalon®

## *TYPICAL PHYSICAL PROPERTIES*

<b>PHYSICAL PROPERTY</b>	<b>UNITS</b>	<b>VALUE</b>
ASTM-D-2000 Classification		CE
Chemical Definition	Chlorosulfonated Polyethylene	
Durometer	<i>(Shore A)</i>	65 +/-5
Tensile Strength	<i>(psi)</i>	1500
Elongation	<i>(% Min)</i>	250
Low Temperature	<i>°F</i>	-30
High Temperature	<i>°F</i>	275
Abrasion Resistance		Excellent
Oil Resistance		Good
Sunlight Aging		Outstanding

The physical properties shown above are typical, but they should not be used to set Quality Control Specification minimum requirements. Please see the CTG Chemical Resistance Guide for general chemical resistance and affect.