



CT Gasket & Polymer Co., Inc.

DEL 8819 Emmott Rd, Houston, TX 77040

MAIL P.O. Box 40940, Houston, TX 77240-0940

TEL (713) 856-8667 / (800) 299-1685

FAX (713) 856-7317

WEB www.ctgasket.com

Neoprene 60 – Cloth Inserted

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	UNITS	VALUE
Ply		1 Ply per 1/8"
Chemical Definition		Poly-Chloroprene
Durometer	<i>(Shore A)</i>	60 +/-5
Tensile Strength	<i>(psi)</i>	800
Elongation	<i>(% Min)</i>	N/A
Low Temperature	<i>°F</i>	-10
High Temperature	<i>°F</i>	200
Abrasion Resistance		Good
Oil Resistance		Good
Sunlight Aging		Good

The physical properties shown above are typical, but they should not be used to set Quality Control Specification minimum requirements. Please see the CTG Chemical Resistance Guide for general chemical resistance and affect.