



CT Gasket & Polymer Co., Inc.

DEL 8819 Emmott Rd, Houston, TX 77040

MAIL P.O. Box 40940, Houston, TX 77240-0940

TEL (713) 856-8667 / (800) 299-1685

FAX (713) 856-7317

WEB www.ctgasket.com

Neoprene 40

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	UNITS	VALUE
ASTM-D-2000 Classification		BC
Chemical Definition		Poly-Chloroprene
Durometer	<i>(Shore A)</i>	40 +/-5
Tensile Strength	<i>(psi)</i>	750
Elongation	<i>(% Min)</i>	350
Low Temperature	<i>°F</i>	-20
High Temperature	<i>°F</i>	220
Abrasion Resistance		Excellent
Oil Resistance		Good
Sunlight Aging		Good

The physical properties shown above are typical, but they should not be used to set Quality Control Specification minimum requirements. Please see the CTG Chemical Resistance Guide for general chemical resistance and affect.