



CT Gasket & Polymer Co., Inc.

TEL (713) 856-8667 / (800) 299-1685

DEL 8819 Emmott Rd, Houston, TX 77040

FAX (713) 856-7317

MAIL P.O. Box 40940, Houston, TX 77240-0940

WEB www.ctgasket.com

SBR - Red Sheet Rubber

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	UNITS	VALUE
ASTM-D-2000 Classification		AA
Chemical Definition		Styrene Butadiene
Durometer	<i>(Shore A)</i>	75 +/-5
Tensile Strength	<i>(psi)</i>	400
Elongation	<i>(% Min)</i>	N/A
Low Temperature	<i>°F</i>	-10
High Temperature	<i>°F</i>	195
Abrasion Resistance		Very Good
Oil Resistance		Poor
Sunlight Aging		Poor

The physical properties shown above are typical, but they should not be used to set Quality Control Specification minimum requirements. Please see the CTG Chemical Resistance Guide for general chemical resistance and affect.